

FIZIČKO-HEMIJSKE OSOBINE GLINA "KOŠARNO"

Gline "Košarno"	Hemijske analize (%)					Skupljanje (%)		Vezivnost N/cm ²	Ostatak na situ 4900 ^o /cm ²	Plastičnost %	Vatrostalnost %
	G. Ž.	SiO ₂	Al ₂ O ₃	Fe ₂ O ₃	Alkalije	pri sušenju 105 ^o C	pri pečenju 1250 ^o C				
K-1	10-15	50-59	25-32	2,0-3,5	1,0-5,0	6,0-9,0	9,0-11,0	110-200	0,3-1,5	40-46	20-31
K-2	9-11	56-60	22-25	2,0-3,5	0,7-4,8	6,0-7,0	6,0-9,0	250-300	12,0-17,0	29-34	20-30
K-3	10-15	49-57	21-27	4,0-7,0	2,6-7,0	80-10	7-9	170-300	1,0-1,6	44-50	17-20
K-5	5-9	63-70	17-22	1,5-2,0	1,7-5,5	4,4-9,0	1,5-2,5	260-320	25-35	20-23	20-28